

## TEST REPORT

Mechanical & Hardgoods Laboratory

Report No. : YAN0117/2018

Page : 1 of 2

Date : DEC. 11, 2018

### Pro-Sight Optical Co., LTD

NO.30, Ln.9, Fude St., Luzhu Dist., Kaohsiung 82146, TAIWAN

### The following merchandise was submitted and identified by the applicant as:

Product Description: LENS

### We have tested the submitted sample(s) as requested and the following results were obtained:

Test Requested: EN 166:2001 Personal eye-protection – Specifications  
Clause 7.3.1 Resistance to surface damage by fine particles (K)  
Clause 7.3.2 Resistance to fogging of oculars (N)

Test Method & Result: --- See following sheet(s) ---

Date of Receipt: NOV. 30, 2018

Testing Period: NOV. 30 ~ DEC. 11, 2018

--- See Next Page ---

Signed for and on behalf of  
SGS Taiwan Ltd.

*Owen Cheng*  
Owen Cheng  
Manager



Laboratory address:  
61, Kai-Fa Road, Nanzih Export Processing Zone, 81170, Kaohsiung, Taiwan

## TEST REPORT

Mechanical & Hardgoods Laboratory

Report No. : YAN0117/2018

Page : 2 of 2

### Test Method & Result:

EN 166:2001 Personal eye-protection – Specifications

### Clause

7.3.1 Resistance to surface damage by fine particles (K)

Result

Pass

### Finding

Sample	Maximum value of the reduced luminance factor	Test Value[(cd/m <sup>2</sup> )/lx]
01	5 (cd/m <sup>2</sup> )/lx	1.80
02		2.56

7.3.2 Resistance to fogging of oculars (N)

Pass

### Finding

The assessed samples were free from fogging for a minimum of 8 seconds.

– Picture(s) –




Photo "A" Appearance of sample

--- End of Report ---